

PACKAGING USES

Food
Healthcare
Media & Electronics
Personal & Beauty Care

Introduction

Printkote is a high quality, coated beached paperboard featuring a market leading stiffness to weigh ratio. Reliable performance and versatility have made Printkote an industry favorite for all types of packaging and printing applications. It meets the needs of today's discriminating brand owners with a bright white, glossy coated side for exceptional printability, and a uniform, smooth uncoated back side. Printkote runs consistently on press, in high-speed converting operations and on filling lines.

FEATURES

Consistency

Surface Uniformity

Fade Resistance

Caliper Range

Stiffness to Weight Ratio

CERTIFICATIONS

Manufacturing Forestry and Procurement

Chain of Custody

Food Contact

Environmental and Safety

CLASSIFICATIONS

Product Type

Mill

BENEFITS

Best-in-class uniformity for optimum runnability on converting and filling equipment which results in maximized throughput and efficiency.

Smooth surface and outstanding ink holdout for excellent printability and consistent brand image.

Classic white styling achieved without the need for Optical Brightening Agents (OBA), resulting in high whiteness without the risk of fading, commonly associated with some OBA grades.

Broad caliper offerings for use across a wide array of packaging and printing applications.

Provides advantage for retailer packaging scorecard and brand owner corporate sustainability programs.

ISO 9001:2008

SFI Standards for Land Management and Wood Procurement (PEFC Endorsed)

SFI Chain of Custody Certified: BV-SFICOC-US08000163

PEFC Chain of Custody Certification: Specific by Application. Contact MWV for Details.

USFDA 21 CFR §176.170 - Contact with Aqueous & Fatty Foods (without restriction)
USFDA 21 CFR §176.180 - Components of Paper and Paperboard in Contact with Dry Food (without restriction)

ISEGA Certificate of Conformity / BFR and EC No. 1935/2004
Acceptable for use with Kosher Foods

US California Proposition 65 Compliant
CONEG Model Heavy Metal and EC/94/62 Article II Compliant
ASTM F 963-95 Toy Safety, EN 71-3 European Toy Safety Compliant
CPSC 16 CFR 1303 Lead Ban Compliant
Elemental Chlorine Free (ECF) Bleached Fiber
RoHS Compliant

Solid Bleached Sulfate, SBS Paperboard, GZ

Covington, VA
Evadale, TX U.S.A.

Grade Availability & Typical Properties (US)												
Grade Availability by Caliper											Units	Method
Caliper (pts)	0.012	0.014	0.015	0.016	0.017	0.018	0.020	0.022	0.024		inches	T-411
Nominal Basis Weight	145	163	172	182	187	199	212	233	250		lb/3000 sqft	T-410
Moisture	5.3	5.3	5.5	5.5	5.5	5.6	5.6	5.6	5.6		percent	T-412
Internal Bond	65	70	70	70	70	70	75	80	85		1/1000 ft-lb	T-833
Stiffness												
Taber 15°	MD	85	135	160	180	205	235	300	385	475	gcm	T-489
	CD	25	65	80	100	115	130	165	205	245	gcm	T-489
Coated Side												
GE Brightness	86	86	86	86	86	86	86	86	86	86	percent	T-452
Gloss	50	50	48	48	46	48	45	45	45	45	percent	T-480
Parker Print	1.0	1.0	1.1	1.2	1.2	1.2	1.2	1.2	1.2	1.2	PPS	T-555
ZDT	52	47	45	45	40	40	40	40	40	40	psi	T-541
Color												
Hunter	L	93	93	93	93	93	93	93	93	93	L-a-b	T-524
	a	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	L-a-b	T-524
	b	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	L-a-b	T-524

Grade Availability & Typical Properties (Metric)

Grade Availability by Weight											Units	Method
Nominal Basis Weight	236	265	280	296	304	324	345	379	407		gsm	T-410
Thickness	305	356	381	406	432	457	509	559	610		microns	T-411
Moisture	5.3	5.3	5.5	5.6	5.5	5.6	5.6	5.6	5.6		percent	T-412
Internal Bond	137	147	147	147	147	147	158	168	179		J/m2	T-833
Stiffness												
Taber 15°	MD	8.3	13.2	15.7	17.7	20.1	23.0	29.4	37.8	46.6	mNm	T-489
	CD	4.4	6.4	7.8	9.8	11.3	12.7	16.2	20.1	24.0	mNm	T-489
Coated Side												
GE Brightness	86	86	86	86	86	86	86	86	86	86	percent	T-452
Gloss	50	50	48	48	46	48	45	45	45	45	percent	T-480
Parker Print	1.0	1.0	1.1	1.2	1.2	1.2	1.2	1.2	1.2	1.2	PPS	T-555
ZDT	358	324	310	310	276	276	276	276	276	276	kPa	T-541
Color												
Hunter	L	93	93	93	93	93	93	93	93	93	L-a-b	T-524
	a	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	L-a-b	T-524
	b	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	1.8	L-a-b	T-524

Stiffness values shown represent measurements at the time of manufacture; field measurements are typically 3-5% higher.



BV-SFICOC-US08000163

For more information, please contact your MWV representative, or visit our website at www.mwv.com.

The information contained in this Product Guide is accurate to the best of MWV's knowledge and belief. It is intended, however, only as an introduction to the typical properties of the product. MWV disclaims any guarantee or warranty with respect to the accuracy of this information or, based on this document, with respect to the suitability of the product for any particular use, including, but not limited to, the compliance of the product with laws, regulations, or standards. © 2009 MeadWestvaco Corporation. MeadWestvaco and Printkote are registered trademarks of MeadWestvaco Corporation. All rights reserved worldwide.

